

Bulk Asbestos Material Analysis

(EPA Method 600/R-93/116, Point Count Analysis)

Sample Company Sample Contact 000 Sample Street Suite 000 Sample City, CA 00000	Client ID: 0000 Report Number: N000000 Date Received: 00/00/0000 Date Analyzed: 00/00/0000 Date Printed: 00/00/0000	
Job ID/Site: Sample Site PLM Report Number: N/A	SGSFL Job ID: 0000-0 Total Samples Submitted: Total Samples Analyzed:	3 3

Sample Preparation and Analysis:

Each sample was prepared using the gravimetric technique. A representative subsample was weighed, ashed for eight hours, and reweighed to determine the proportion of the organic component. The ashed residue was ground in concentrated hydrochloric acid, dried and reweighed to determine the acid-soluble component weight percentage. The residual material was analyzed for asbestos using polarized light microscopy. Asbestos quantitation was performed using the semi-quantitative Point Count method following the general guidelines in EPA Method 600/R-93/116. The analytical sensitivity for the method is calculated as the asbestos concentration that results from one point counted in the analysis adjusted using the residual weight of the sample. The limit of detection for this method has not been determined.

Sample ID	Lab Number	Sample Description		
1	00000000	White Plaster		
Point Count Results:			Gravimetry Results:	
Number of asbestos points cour	nted:	2	Organic weight percentage:	10.72
Number of non-empty points:		1000	Acid-soluble weight percentage	12.45
Percent asbestos in layer:		0.15	Residual weight percentage:	76.82
Analytical sensitivity (%):		0.08		
Asbestos type(s) detected:	Chrysoti	le		
2	00000000	White Plaster		
2 Point Count Results:	00000000	White Plaster	Gravimetry Results:	
_		White Plaster	Gravimetry Results: Organic weight percentage:	10.29
Point Count Results:	nted:		•	10.29 12.85
Point Count Results: Number of asbestos points cour	nted:	3	Organic weight percentage:	
Point Count Results: Number of asbestos points cour Number of non-empty points:	nted:	3 1000	Organic weight percentage: Acid-soluble weight percentage	12.85



Bulk Asbestos Material Analysis

(EPA Method 600/R-93/116, Point Count Analysis)

Sample Company Sample Contact 000 Sample Street Suite 000 Sample City, CA 00000	Client ID: Report Number: Date Received: Date Analyzed: Date Printed:	0000 N000000 00/00/0000 00/00/0000 00/00/0000
Job ID/Site: Sample Site	FALI Job ID: Total Samples Subm	0000-0
PLM Report Number: N/A	Total Samples Subm Total Samples Analy	

Sample Preparation and Analysis:

Each sample was prepared using the gravimetric technique. A representative subsample was weighed, ashed for eight hours, and reweighed to determine the proportion of the organic component. The ashed residue was ground in concentrated hydrochloric acid, dried and reweighed to determine the acid-soluble component weight percentage. The residual material was analyzed for asbestos using polarized light microscopy. Asbestos quantitation was performed using the semi-quantitative Point Count method following the general guidelines in EPA Method 600/R-93/116. The analytical sensitivity for the method is calculated as the asbestos concentration that results from one point counted in the analysis adjusted using the residual weight of the sample. The limit of detection for this method has not been determined.

,	00000000	White Plaster		
Point Count Results:			Gravimetry Results:	
Number of asbestos poin	Number of asbestos points counted: 2		Organic weight percentage:	10.57
Number of non-empty po	oints:	000	Acid-soluble weight percentage	13.61
Percent asbestos in laye	er: 0	0.15	Residual weight percentage:	75.82
Analytical sensitivity (%):	0.08		
Asbestos type(s) detected	d: Chrysotile	;		

Laboratory Supervisor, Hayward Laboratory

Analytical results and reports are generated by SGS Forensic Laboratories (SGSFL) at the request of and for the exclusive use of the person or entity (client) named on such report. Results, reports or copies of same will not be released by SGSFL to any third party without prior written request from client. This report applies only to the sample(s) tested. Supporting laboratory documentation is available upon request. This report must not be reproduced except in full, unless approved by SGSFL. The client is solely responsible for the use and interpretation of test results and reports requested from SGSFL SGSFL is not able to assess the degree of hazard resulting from materials analyzed. SGS Forensic Laboratories reserves the right to dispose of all samples after a period of thirty (30) days, according to all state and federal guidelines, unless otherwise specified. All samples were received in acceptable condition unless otherwise noted.